


E-glass Multiaxial Fabrics

Product Code: E-BXM800/300

Version: 2015

Page 1 of 1



E-BXM800/300

Fiber Type: E-Glass

Architecture: Double Biaxial($\pm 45^\circ$) With Mat

Total Weight: 32.74oz/sq.yd / 1110 g/sq.m

Roll Specifications			Fiber Architecture Data
Roll Width 50 in. / 1270 mm	Roll Weight 110 lbs / 50 kg	Roll Length 38 yd / 35 m	+45°: 11.83oz/sq.yd / 401 g/sq.m -45°: 11.83oz/sq.yd / 401 g/sq.m Mat: 8.85oz/sq.yd / 300 g/sq.m
Acceptance Limits: ± 5 mm	± 2%	± 0.5 m	
Technical Parameters			
Area Weight (g/m ²)	Moisture Content (%)	Loss on Ignition (%)	
1110 (±5%)	≤0.20	0.2—1.0	

*Packaging: Bag with polyester film, Carton on Pallet.

**Total weight refers to reinforcement material only (does not include stitching weight).

***Storage: Unless otherwise specified, fiberglass products should be stored in a dry, cool and rain-proof area. The room temperature and humidity should be always maintained at 15℃~35℃ and 35%~65% respectively.