


E-glass Multiaxial Fabrics

Product Code: E-BXM600/225

Version: 2015

Page 1 of 1



E-BXM600/225

Fiber Type: E-Glass

Architecture: Double Biaxial($\pm 45^\circ$) With Mat

Total Weight: 24.63oz/sq.yd / 835 g/sq.m

Roll Specifications

| | | |
|--------------------|-----------------|--------------|
| Roll Width | Roll Weight | Roll Length |
| 50 in. / 1270 mm | 110 lbs / 50 kg | 51 yd / 47 m |
| Acceptance Limits: | | |
| ± 5 mm | $\pm 2\%$ | ± 0.5 m |

Fiber Architecture Data

| |
|--|
| +45°: 8.88oz/sq.yd / 301 g/sq.m |
| -45°: 8.88oz/sq.yd / 301 g/sq.m |
| Chopped Mat: 6.64oz/sq.yd / 225 g/sq.m |

Technical Parameters

| | | |
|---------------------|------------------|------------------|
| Area Weight | Moisture Content | Loss on Ignition |
| (g/m ²) | (%) | (%) |
| 835 ($\pm 5\%$) | ≤ 0.20 | 0.2—1.0 |

*Packaging: Bag with polyester film, Carton on Pallet.

**Total weight refers to reinforcement material only (does not include stitching weight).

***Storage: Unless otherwise specified, fiberglass products should be stored in a dry, cool and rain-proof area. The room temperature and humidity should be always maintained at 15 $^{\circ}$ C~35 $^{\circ}$ C and 35%~65% respectively.