


E-glass Multiaxial Fabrics

Product Code: E-LT600

Version: 2015

Page 1 of 1



E-LT600

Fiber Type: E-Glass
 Architecture: 0°/90° Biaxial
 Total Weight: 18.37oz/sq.yd / 623 g/sq.m

Roll Specifications			Fiber Architecture Data
Roll Width 50 in. / 1270 mm	Roll Weight 110 lbs / 50 kg	Roll Length 69 yd / 63 m	0°: 9.73oz/sq.yd / 330 g/sq.m 90°: 8.44oz/sq.yd / 286g/sq.m
Acceptance Limits: ± 5 mm	± 2%	± 0.5 m	
Technical Parameters			
Area Weight (g/m ²)	Moisture Content (%)	Loss on Ignition (%)	
623 (±5%)	≤0.20	0.2—1.0	

*Packaging: Bag with polyester film, Carton on Pallet.

**Total weight refers to reinforcement material only (does not include stitching weight).

***Storage: Unless otherwise specified, fiberglass products should be stored in a dry, cool and rain-proof area. The room temperature and humidity should be always maintained at 15c~35c and 35%~65% respectively.