


E-glass Multiaxial Fabrics

Product Code: E-QX1200

Version: 2015

Page 1 of 1



E-QX1200

Fiber Type: E-Glass
 Architecture: Quadraxial (0°/+45°/90°/-45°)
 Total Weight: 35.69oz/sq.yd / 1210g/sq.m

Roll Specifications			Fiber Architecture Data
Roll Width	Roll Weight	Roll Length	0° : 8.88oz/sq.yd / 301 g/sq.m
50 in. / 1270 mm	110 lbs / 50 kg	62 yd / 32 m	+45°: 8.88oz/sq.yd / 301 g/sq.m
Acceptance Limits:			90° : 8.86oz/sq.yd / 300 g/sq.m
±5 mm	±2%	±0.5 m	-45° : 8.88oz/sq.yd / 301 g/sq.m
Technical Parameters			
Area Weight	Moisture Content	Loss on Ignition	
(g/m ²)	(%)	(%)	
1210 (±5%)	≤0.20	0.2—1.0	

*Packaging: Bag with polyester film, Carton on Pallet.

**Total weight refers to reinforcement material only (does not include stitching weight).

***Storage: Unless otherwise specified, fiberglass products should be stored in a dry, cool and rain-proof area. The room temperature and humidity should be always maintained at 15°~35°c and 35%~65% respectively.